


## Pan Head - Type I (Phillips) Combination Sltd - A, AB







THREAD DATA		
<b>Size:</b> #12	Threads per in.: 14	Thread Class or Type: AB
Major Diameter: 0.2150 - 0.2080	Minor Dia Max/Min.: 0.164 - 0.157	<b>Standard:</b> ASME B18.6.3-2013
DIMENSIONAL DATA		
<b>Type:</b> Pan Head - Type I (Phillips) Combination Sltd - A, AB	<b>Standard:</b> ASME B18.6.3 - 2013	Nominal Diameter: 0.216
<b>A - Head Diameter:</b> 0.425 - 0.407	<b>H - Head Height:</b> 0.151 - 0.139	<b>J - Slot Width:</b> 0.067 - 0.056
T - Slot Depth: 0.077 - 0.055	Driver Size: 3	Penetration Depth: 0.124 - 0.098
Wobble: 10°	M - Ref. Recess Dim.: 0.252	L - Length: 1-1/4
Length Tolerance: ± 0.05		
PHYSICAL REQUIREMENTS		
Nominal: 0.216	Standard: ASME B18.6.3-2013, Type AB (carbon steel)	Typical Materials: carbon steel: 1018-1022
Test Plate Thickness in.: 0.1270 - 0.1230	Test Plate Hole Size in.: 0.1875	Torsional Strength, Min. (in.lbf): 88
Core Hardness: HRC 28 - 38	Case Hardness: HRC 45 Min.	Case Depth (in.): .009004
Ductility Test Angle: 10°	Straightness Factor: N/A	
FINISH DATA		
Finish: Zinc & Clear, non-hexavalent/Cr(VI) free -	K factor (ref. DIN 946): 0.22	Standard: ASTM F1941/F1941M-2016, Fe/Zn 3AN

<sup>&</sup>lt;sup>1</sup> These torque values are based on K factors determined using DIN 946, tightening tension of 75% of the yield strength, and the calculation formula T=KDP. These values are advisory only. The torque for assembling critical joints should be determined and/or verified through actual experimentation by the user. The IFI is not responsible for any losses or claims resulting from the use of these values. <sup>2</sup> Calculated Pretension is equal to 75% of the bolt's yield strength achieved when using the indicated Tightening Torque.



.0001"/ 3µm

