

GRADE MARK

Threads per in.: 16	Series Designation: UNC
Major Diameter: 0.3737 - 0.3643	Pitch and Functional Dia.: 0.3331 - 0.3287
Standard: ASME B1.1 - 2003 (R2008)	Length: 1
Standard: IFI - 199	Nominal Diameter: 0.375
G - Width Across Corners: 0.650 - 0.620	R - Fillet Radius: 0.030 - 0.010
Point Type: Non-pointed	
Standard: ASTM A307A-2014	Typical Materials: low carbon steel, 1006 through 1022
Tensile Load, Min. (lbf): 4,650	Yield PSI, 2% Offset, Machined Specimen: 36,000
Tensile Strength, Min. (psi): 60,000	Calculated Shear Load-BODY (ref.)(lbf): 2,790
Straightness Factor: N/A	Calculated Pretension <sup>2</sup> (lbf) : 2,093
K factor (ref. DIN 946): 0.22	<b>Standard:</b> ASTM F1941/F1941M-2016, Fe/Zn 3AN
	Major Diameter: 0.3737 - 0.3643Standard: ASME B1.1 - 2003 (R2008)Standard: ASME B1.1 - 2003 (R2008)G - Width Across Corners: 0.650 - 0.620Point Type: Non-pointedStandard: ASTM A307A-2014Tensile Load, Min. (Ibf): 4,650Tensile Strength, Min. (psi): 60,000Straightness Factor: N/A

<sup>1</sup> These torque values are based on K factors determined using DIN 946, tightening tension of 75% of the yield strength, and the calculation formula T=KDP. These values are advisory only. The torque for assembling critical joints should be determined and/or verified through actual experimentation by the user. The IFI is not responsible for any losses or claims resulting from the use of these values.<sup>2</sup> Calculated Pretension is equal to 75% of the bolt's yield strength achieved when using the indicated Tightening Torque.



