
## Round Head- Type I (Phillips) - Combination Sltd



This type of recess has a large center opening, tapered wings, and blunt bottom, with all edges relieved or rounded. A slot crosses the head aligned with one pair of wings.



## **GRADE MARK**

THREAD DATA		
<b>Size</b> : #6	Threads per in.: 32	Series Designation: UNC
Thread Class or Type: 2A	Major Diameter: 0.1372 - 0.1312	Pitch and Functional Dia.: 0.1169 - 0.1141
Tensile Stress Area: 0.0091	<b>Standard:</b> ASME B1.1 - 2003 (R2008)	Length: 1-1/2
Length Tolerance: -0.06		
DIMENSIONAL DATA		
<b>Type:</b> Round Head- Type I (Phillips) - Combination Sltd	<b>Standard:</b> ASME B18.6.3 - 2013	Nominal Diameter: 0.138
<b>A - Head Diameter:</b> 0.260 - 0.240	H - Head Height: 0.103 - 0.091	<b>J - Slot Width:</b> 0.048 - 0.039
T - Slot Depth: 0.068 - 0.051	Driver Size: 2	Penetration Depth: 0.073 - 0.045
Wobble: 12°	M - Ref. Recess Dim.: 0.155	
PHYSICAL REQUIREMENTS		
Nominal: 0.138	Standard: ASME B18.6.3-2013, Machine Screw (carbon steel)	Typical Materials: low carbon steel, 1010 through 1022
Hardness: HRB 100 - 70	Tensile Load, Min. (lbf): 545	Yield PSI, 2% Offset, Machined Specimen: 36,000
Tensile Strength, Min. (psi): 60,000	Calculated Shear Load-BODY (ref.)(lbf): 327	Calculated Shear Load-THREADS (ref.)(lbf): 273
Straightness Factor: N/A	Calculated Pretension <sup>2</sup> (lbf): 246	Tightening Torque <sup>1</sup> : 1 ft.lbf, 7 in.lbf, 0.8 Nm
FINISH DATA		
Finish: Zinc & Clear, non-hexavalent/Cr(VI) free0001"/ $3\mu m$	K factor (ref. DIN 946): 0.22	<b>Standard:</b> ASTM F1941/F1941M-2016, Fe/Zn 3AN

<sup>&</sup>lt;sup>1</sup> These torque values are based on K factors determined using DIN 946, tightening tension of 75% of the yield strength, and the calculation formula T=KDP. These values are advisory only. The torque for assembling critical joints should be determined and/or verified through actual experimentation by the user. The IFI is not responsible for any losses or claims resulting from the use of these values.<sup>2</sup> Calculated Pretension is equal to 75% of the bolt's yield strength achieved when using the indicated Tightening Torque.



